

# RECELL-DIRECT CATHODE RECYCLING: MATERIAL SEPARATION AND PREPARATION

Project ID: bat464



**ALBERT LIPSON**

Argonne National Laboratory

2021 DOE Vehicle Technologies Office  
Annual Merit Review  
June 21-25, 2021

This presentation does not contain any proprietary, confidential, or otherwise restricted information

# PROJECT OVERVIEW

## Timeline

- Project start: October 2018
- Project end: September 2021
- Percent complete: ~90%

## Budget

FY19	\$4,615k
FY20	\$5,150k
FY21	\$4,915k

## Barriers


- Recycling and Sustainability
  - Cost to recycle is currently 5-15% of battery cost
  - Material shortage (Li, Co, and Ni)
  - Varying chemistries result in variable backend value

## Partners

- Argonne National Laboratory
- National Renewable Energy Laboratory
- Oak Ridge National Laboratory
- University of California, San Diego
- Worcester Polytechnic Institute
- Michigan Technological University


# RELEVANCE

By 2025, reduce the cost of EV battery packs to less than \$100/kWh with technologies that **significantly reduce or eliminate the dependency on critical materials (such as cobalt) and utilize recycled material feedstocks.**



# RELEVANCE

- Lower cost of batteries
- Enable lower environmental impacts
- Increase our country's energy security




# APPROACH

## ReCell's Mission:

Decrease the cost of recycling lithium-ion batteries to ensure future supply of critical materials and decrease energy usage compared to raw material production

Direct recycling minimizes steps back to use



# APPROACH

Year 1 – Bench scale testing:  
Powder-to-Cell



Year 2 – Start to scale up  
unit operations



Year 3 – Finish scale up and  
show cell-to-cell recycling

- Binder Removal
- Cathode/ Cathode Separation
- Relithiation
- Cathode Upcycling
- Impurity Impact



**DIRECT  
CATHODE  
RECYCLING**

**OTHER  
MATERIAL  
RECOVERY**



- Cell Shredding
- Electrode Delamination
- Anode/ Cathode Separation
- Electrolyte Component Recovery

**Cross Cutting Projects**

- Cell Design for Rejuvenation



**DESIGN  
FOR  
SUSTAINABILITY**

**MODELING  
AND  
ANALYSIS**




- EverBatt (TEA/LCA)
- LIBRA (Supply Chain Modeling)

*Program does not include battery dismantling, transportation, or 2<sup>nd</sup> use*

# APPROACH

- Multiple processes investigated to mitigate risk
- Continual review of new project ideas
- End projects that are not showing promise in cost and performance
- These processes can benefit other recycling processes

## Typical Direct Recycling Process Flow



# MILESTONES

- |         |          |   |
|---------|----------|---|
| FY20 Q3 | Complete | Down-select solvent(s) to separate black mass from current collector and optimize the process conditions to achieve >90% recovery of black mass   |
| FY20 Q4 | Complete | Demonstrate recovery of anode and cathode powders using the new pilot scale froth column  |
| FY21 Q1 | Complete | Preliminary report of sensitivity analysis of battery recycling in the LIBRA model focusing on outputs including the number of recycling plants built and the percentage of batteries recycled over time. |
| FY21 Q2 | Complete | Demonstrate 30% graphene yield from spent anode using a Taylor Vortex Reactor   |
| FY21 Q3 | Ongoing  | Final report on performance and cost modeling of directly recycled manufacturing scrap  |
| FY21 Q4 | Ongoing  | Provide preliminary cost analysis, yield, and efficiency on the separation-relithiation conditions on NMC spent electrodes via solvent-based dual process   |

Each Individual project has its own milestones, though not listed here.




# APPROACH TO SEPARATION AND PREPROCESSING

- Minimize contamination
- Recover as many materials as possible
- Keep processing costs low
- Reduce waste streams
- Understand the role of remaining contaminants
- Develop solutions to problematic contamination
- Develop multiple solutions to increase likelihood that a complete working process can be developed



# HAMMERMILLING vs. SHREDDING


Fine Particle Contamination from Size Reduced, Dry Pouch Cells



Dual Shaft Shredder





Hammer Mill



# RECOVERING ELECTROLYTE

- Electrolyte can be recovered using additional carbonate solvent after shredding
- Tested different end-of-life commercial electrolytes to see if they could be recovered and made into a new cell
- Recovered electrolytes perform close to baseline electrolytes
- Tested different purification methods




# REMOVING SEPARATOR

## Aspirator and Cyclone

- Separated components using an aspirator/cyclone by controlling air flow
- Light, non-bound plastics can be easily removed


Light Fraction



Heavy Fraction



Some separator is still present in bound clumps of shredder residue




# SOLVENT BASED ELECTRODE RECOVERY

## Cathode Scrap



- Demonstrated the direct recycling and re-manufacturing of cathode scraps using SolveX process
- Re-processed the recovered cathode films for new cathode coating
- Proved that SolveX process does no damage to the active materials, does not corrode the current collectors, and has negligible influence on electrochemical performance

↓ New cell






# SOLVENT BASED ELECTRODE RECOVERY

## Anode Scrap




- Demonstrated the recovery of anode material using SolveX process
- Reprocessed the recovered anode material into new anode coating
- Results show that SolveX process does not damage the active materials
- recovered materials have similar electrochemical performance to virgin material




# AQUEOUS SEQUENTIAL SEPARATION

- Separate electrode materials from foils to sequentially recover anode from cathode
- Reduced cost and simplicity of a single mixing vessel process
- Identified the optimal composition of the aqueous solution containing buffer and additive X
- Developed a process to separate electrode materials from current collectors in a water solution



# THERMAL BINDER REMOVAL IN A CONTINUOUS ROTARY KILN

- Continuous rotary kiln process results in improved performance compared to a batch rotary kiln or a box furnace
- Easily scalable and simple




NMC 111 mixed with 3 wt.% PVDF  
and 5 wt.% carbon black processed at  
500°C with 0 or 4 wt.% LiOH·H<sub>2</sub>O




# SEPARATION OF ANODE AND CATHODE

- A separation technique has been used to separate a 1:1 mixture (by weight) of anode on copper foil from cathode on aluminum foil
- Three size fractions (similar to those obtained after shredding)
- Additional studies show that using Process A again on the separated material can further improve separation efficiency
- Decreased separation efficiency of large pieces, 1-1.5", is due to the size of the lab-scale equipment


## ~1/4" Electrodes





## 0.5-1" Electrodes



## 1-1.5" Electrodes



# SOLVENT-BASED GRAVITY SEPARATION



## Multistage Separation

Product	NMC111 (%)	Graphite (%)
Tail	0.60%	99.40%
Conc	99.03%	0.97%



$$SI = R(NMC111) - R(Graphite)$$

- Alternative to the previously demonstrated froth flotation process for anode/cathode separation
- Centrifugal gravity separation was used to separate a mixture of the pristine graphite and NMC111 powders.
- Over 90% of NMC111 is collected within the concentrator, and the recovery of graphite within the concentrator varies significantly with feed mass.
- After multistage separation processes, the concentrate product consisted of 99% of NMC111

# ELECTROMAGNET

## Separation of Cathode Mixtures

- Multistage magnetic separation can improve purity
- After the 3<sup>rd</sup> stage, the yield of the magnetic fraction is 18% and contains 85% pure LMO
- Potential to be used as a cleanup step



### Separation Conditions:



**Slurry = 5 wt.% solid loading  
(LMO:NMC111:NCA, 1:1:1)**

**Magnetic Strength = 2 Tesla**


**Slurry mixed in reservoir at  
200 RPM for 2 min.**

# CATHODE/CATHODE SEPARATION BY FROTH FLOTATION

Initial processing in a bench scale Denver cell



Scale up in a froth column




- Froth flotation experiments were conducted using a rougher-cleaner circuit to separate a mixture of pristine NMC111 and LMO materials
- The grade of the NMC111 in the froth product reached 95-97% at a recovery rate of 80-90% after two flotation steps
- The tailing consisted of 90-98% of LMO by weight at a recovery rate of 95% or above
- Works well with other binary mixtures, such as NCA/LMO, LCO/LMO, and NMC111/NMC622

# CARBON IMPURITY AFFECT DURING COPRECIPITATION

Tap density (g/ml) of precursors at different times


Sample	3hrs	6hrs	9hrs	12hrs
VNCM	0.65	1.01	1.45	1.85
0.2CNCM	0.86	1.51	1.70	1.92
1CNCM	0.89	1.51	1.75	1.86
5CNCM	0.95	1.47	1.76	1.83

- Carbon impurity accelerates the precipitation increasing initial tap density



SEM cross-sectional images of (a) CNCM precursor with EDS carbon signal and (b) CNCM cathode

- Carbon nano-particles are observed inside precursor, and after sintering, cathode particles with central pore are formed




Rietveld refinement results of NCM622 cathodes


Sample	a-axis (Å)	c-axis (Å)	volume (Å <sup>3</sup> )	Ni <sub>Li</sub> (%)	χ <sup>2</sup>
VNCM	2.865	14.214	101.04	3.84	2.78
0.2CNCM	2.867	14.220	101.25	3.93	2.75
1CNCM	2.867	14.219	101.24	4.01	2.87
5CNCM	2.867	14.224	101.31	4.18	2.90

- No impurity peaks in XRD pattern
- Cation mixing degree increases with C content, which hinders electrochemical performance.

# BLACK MASS PURIFICATION: MOTIVATION & OVERVIEW




- Shredded black mass contains trace **Al** & **Cu**: potentially has safety impacts and reduces the performance of recycled material
- Identify** and **optimize** BM purification process to enable **complete and rapid dissolution** of solid contaminants (Al, Cu) **without adversely impacting** structure or electrochemical performance of NMC






# BLACK MASS PURIFICATION: HIGHLIGHTED RESULTS

## Al Corrosion




- Aluminum corrosion is accelerated via elevated temperature and kinetic enhancement in alkaline solution
- Full corrosion achieved in **5 min** (40 °C w/ kinetic enhancement; pH 13)

## Cu Corrosion



- Exploring use of chemical enhancer; chelating agent; kinetic enhancer; and elevated temperature to improve kinetics and thermodynamics
- >93%** corrosion demonstrated to date; improvements ongoing

## Impacts on NMC



- Purification treatment **does not significantly impact** electrochemical performance of NMC

# SUMMARY AND FUTURE WORK

- Processes have been developed to enable pure cathode to be recovered as a feedstock for relithiation and upcycling
- Minimizing contamination at every stage of the process is needed to retain the material performance
  - Continuing to evaluate the effects of contamination and find ways to eliminate it if it is unavoidable
- Many different separation modalities have been found that with a correctly designed process can give high purity with high yields
- We are working to scale up these processes to kg quantities and more
  - Shredder to be installed shortly
  - Froth column being optimized for anode/cathode and cathode/cathode separations
- We are applying these processes to manufacturing scrap, which can enable their implementation before significant quantities of end-of-life batteries are available for recycling
- Developing an overall recycling process that recovers as much material as possible, at the lowest processing cost, and with cathode that has comparable performance to the pristine



# RESPONSE TO REVIEWERS

Not reviewed last year

# COLLABORATION AND ACKNOWLEDGEMENTS

Support for this work from the Office of Vehicle Technologies,  
DOE-EERE, is gratefully acknowledged –  
Samm Gillard, Steven Boyd, and David Howell



Michigan  
Technological  
University



WPI



UC San Diego

Shabbir Ahmed (Argonne)  
Yaocai Bai (ORNL)  
Jon Becker (NREL)  
Ilias Belharouak (ORNL)  
Ira Bloom (Argonne)  
Anthony Burrell (NREL)  
Zheng Chen (UCSD)  
Andrew Colclasure (NREL)  
Jaclyn Coyle (NREL)  
Qiang Dai (Argonne)  
Sheng Dai (ORNL)  
Alison Dunlop (Argonne)  
Jessica Durham (Argonne)  
Rachid Essehli (ORNL)  
Kae Fink (NREL)  
Tinu Folayan (MTU)  
Linda Gaines (Argonne)

Andy Jansen (Argonne)  
Sergiy Kalnaus (ORNL)  
Matt Keyser (NREL)  
Greg Krumdick (Argonne)  
Michael LeResche (Argonne)  
Jianlin Li (ORNL)  
Albert Lipson (Argonne)  
Huimin Luo (ORNL)  
Josh Major (NREL)  
Margaret Mann (NREL)  
Tony Montoya (Argonne)  
Helio Moutinho (NREL)  
Lei Pan (MTU)  
Kyusung Park (NREL)  
Haruka Pinegar (Argonne)  
Bryant Polzin (Argonne)  
Kris Pupek (Argonne)

Vicky Putsche (NREL)  
Shriram Santhanagopalan (NREL)  
Jeff Spangenberg (Argonne)  
Venkat Srinivasan (Argonne)  
Nathaniel Sunderlin (NREL)  
Steve Trask (Argonne)  
Jack Vaughey (Argonne)  
Patrick Walker (NREL)  
Tao Wang (ORNL)  
Yan Wang (WPI)  
Dustin Weigl (NREL)  
Olumide Winjobi (Argonne)  
Zhenzhen Yang (Argonne)  
Jiuling Yu (NREL)  
Xiaolu Yu (UCSD)  
Ruiting Zhan (MTU)

